

	Imperial (inches)		Metric (mm)	
	Width	Thickness	Width	Thickness
Hot Rolled Sheet and Strip:				
Algoma	¾-96	0.060-0.500	19-2439	1.22-12.7
Dofasco	to 60	0.059-0.500	to 1525	1.5-12.7
IPSCO	36-72	0.060-0.750	914-1800	1.6-19
Sidbec-Dosco	to 60	0.059-0.375	to 1525	1.5-9.5
Stelco	18-72	0.064-0.625	457-1829	1.626-15.87
Cold Rolled Sheet and Strip:				
Algoma	¾-74	0.015-0.125	19-1880	0.38-3.18
Atlas Stainless ⁽⁶⁾	to 49.2	0.015-0.187	to 1250	0.43-4.76
Dofasco	to 60	0.015-0.138	to 1525	0.381-3.50
Sidbec-Dosco	to 50.5	0.015-0.120	to 1283	0.381-3.04
Stelco	18-72	0.013-0.142	457-1829	0.330-3.607
Electrical Steels (Silicon):				
Dofasco	to 44	0.011-0.014	to 1117	0.27-0.35
Galvanized:				
Dofasco ⁽⁹⁾	2.95-60	0.012-0.167	75-1525	0.305-4.242
Stelco	20-60	0.010-0.168	508-1525	0.254-4.270
Tin Mill Products:				
Single Reduced				
Dofasco	20-38	0.008-0.015	508-965	0.203-0.38
Stelco	18 3/16-42¼	0.008-0.015	462-1073	0.203-0.38
Double Reduced				
Dofasco	20-38	0.006-0.011	508-965	0.15-0.28
Stelco	18 3/16-41¼	0.006-0.011	462-1073	0.15-0.28
Tin Free Steel (Electrolytic chrome)				
Dofasco	20-38	0.006-0.015	508-965	0.15-0.38
Stelco	20¼-42¼	0.006-0.0141	514-1073	0.15-0.36
Prepainted Steels:				
Dofasco	to 60	0.012-0.052	to 1524	0.30-1.321
Stelco	to 60	0.010-0.052	to 1524	0.254-1.321