

Samples of White Lead in Oil—*Concluded.*

RESULTS OF ANALYSIS.				No. of Sample.	Remarks of Official Analyst.
Lead Oxide.	Carbon Dioxide.	Barium Sulphate.	Oil.		
p. c.	p. c.	p. c.	p. c.		
52.47	7.16	29.66	7.92	17320	Adulterated.
27.13	3.78	58.24	7.99	17321	"
86.80	8.60	.....	6.60	21568	Genuine.
72.87	10.65	15.00	7.70	21569	Barium added; adulterated.
75.44	5.85	11.50	7.70	21570	"
74.69	7.10	.....	6.50	21571	Genuine.
87.87	11.40	.....	6.80	21572	"
75.32	4.10	78.00	9.90	21573	Adulterated with barium sulphate.
86.67	10.80	.....	5.70	21574	Genuine.
47.15	7.55	45.70	6.30	21575	Adulterated with barium sulphate.
85.20	11.90	.....	7.10	21576	Genuine.
86.30	11.40	.....	7.00	21577	"
17.57	2.40	70.30	9.30	21578	Adulterated with barium sulphate.