

FROM COAL BROOK.			FROM KELVIN BROOK.	
	No. 3.	No. 4.	No. 1.	
Moisture	9.93	5.02	8.44	
Volatile Matter.....	24.01	31.25	28.54	
Fixed Carbon	49.15	54.03	5.07	
Ash	16.14	8.66	11.53	
Sulphur77	1.04	1.42	
	100.000	100.000	100.000	
Coke in closed vessel	66.06	63.73	63.92	

FROM BAY ST. GEORGE.

	Clary Seam	Jukes Seam	Howley Seam	Shears Seam
Moisture.....	3'548	3'036	2'784	4'90
Volatile matter.....	30'897	30'344	29'784	33'12
Fixed Carbon	55'229	60'142	54'468	not given
Sulphur.....	3' 944	1' 963	3'047	0'44
Ash.....	6'380	4'515	10'430	3'16
	100'000	100'000	100'000	Coke 61'371*

* The evaporative power of this coal expressed in pounds of water evaporated by one lb of coal at 212 F. was 12.371, which considerably exceeds that of North Sydney, or the best Scotch, Walsh or English coals.