

CLAYS

Museum No.	Locality.	Grinding Properties.	Colour when Ground in Oil.	Body.	Colour when Ground in Oil.	Body.	Texture of Surface.	Extent of Clay.
<i>New Scotland.</i>								
5172	King's Co.	Slightly gritty in grinding.	Brown.	2	Reddish brown.	2	Smooth.	B. T. Said to be of great depth.
5237	Avonport Pictou Co.	"	"	3	Yellow brown.	3	"	"
6684	Salt springs, Dochester, Pictou Co.	"	Cherry.	3	Burnt sienna.	3	"	"
<i>McKenzie Brook, Middle Musquodoboit.</i>								
5126	Cumberland Co.	Easy and no grit.	Raw sienna.	2	Dark burnt sienna.	2	"	"
3901	River Denys, Antigonish Co.	Gritty in grinding.	Grey.	4	Brown pink.	3	"	"
5391	Antigonish Co.	Slightly gritty in grinding.	Brown.	2	Dark venetian red.	2	"	"
<i>Prince Edward Island.</i>								
1937	Mouth of harbour, Charlottetown.	Gritty in grinding.	Brown pink.	3	Brownish red.	3	"	"
<i>New Brunswick.</i>								
1918	Fredericton.	Easy and no grit.	Brown yellow.	2	Yellowish brown.	2	Smooth.	B. T. About twenty feet.
1949	Fryville.	"	Brown.	2	Brown red.	2	"	"
1950	Louisville.	Gritty in grinding.	"	2	"	2	"	"