

For steaming your wood for the bows, rock elm requires about twenty minutes, with a slow boil. Hickory requires to be boiled slowly for about thirty minutes.