

JORDAN PETROLEUM REFINERY CO. LTD.

LABORATORY

Certificate No. \_\_\_\_\_  
 Date Issued \_\_\_\_\_  
 Tank No. \_\_\_\_\_  
 Sampling Date: \_\_\_\_\_

SPECIFICATIONS

**Gasoline**  
REGULAR

TESTS		RESULTS	METHODS
Distillation			ASTM D-86
Fuel Recovered			
10% Vol.	@ °C	60 Max.	
50% Vol.	@ °C	120 Max.	
90% Vol.	@ °C	180 Max.	
End Point	°C	205 Max.	
Vapor Pressure @ 100 °F	kg/cm <sup>2</sup>	0.7 Max.	ASTM D-323
Color		Standard Red.	
Total Sulfur	% wt.	0.2 Max.	ASTM D-1268
Corrosion, Copper (3hr. at 50°C) Classification		NO. 1 Strip.	ASTM D-130
Oxidation Stability	Minutes	360 Min.	ASTM D-525
Existent Gum	mg/100cc.	4.0 Max.	ASTM D-381
TBL Content	CC/USG	3.0 Max.	ASTM D-3341
Octane No. R. M.		88	ASTM D-2699
Remarks :			

Chief Chemist

*M. J. ...*  
11/1/94