


Assays made by Cronan & Gillespie, assayers, Rossland, for G. E. Pfunder, on account of Colonna mine:



DATE. 1895.	DESCRIPTION.	GOLD.	COPPER. Per cent.
Oct. 3—	Soft oxidized rock from ledge No. 1	\$ 7 50	
	Hard iron from ledge No. 2	Trace	
Oct. 8—	Black oxide ore from ledge No. 1, shaft	33	
Oct. 9—	Soft, yellow oxidized matter, from ledge No. 1.....	65	
	Black oxide ore, ledge No. 1.....	33	37½
	Small pieces same.....	38 20	
Oct. 10—	Black oxide ore from ledge No. 1	38 20	24½
	Soft, red ore, ledge No. 1.....	84 80	
	Drillings, ledge No. 2	Trace	
Oct. 13—	Footwall, shaft.....	7 60	
	Hanging wall, shaft	7 60	

The above are not picked assays, but are *all* the assays ever made from ore from the Buckeye. The Buckeye is the first mining property in the camp to be placed on the market with a body of pay ore