

INSERTED BY THE MEMBERS OF TORONTO DENTAL SOCIETY FOR DR. BLACK'S CLINIC BEFORE
THE ONTARIO DENTAL SOCIETY.

No.	MADE BY DOCTOR	NAME OF ALLOT.	TIME	MOVEMENT IN POINTS	MICROSCOPIC	REMARKS.
1	G. V. Black	Fellowship	Z	Ex. 11; Cn. 1	Very slight crack	This was an experimental sample annealed a long time.
2	F. B. Noyes	Frost white (Dr. Kester)	A. E.	Ex. 1; Ex. 4	Perfect	2 weeks old, not annealed, coarse cut.
3	J. B. Wilmoth	Silver (1; tin 22; copper 5)	C. F.	Ex. 2; Cn. 1	White crack	Annealed, fine cut.
4	"	"	H. B.	Ex. 2; Cn. 1	Perfect	No excess of mercury in packing.
5	"	Robertson's	C. M.	Cn. 1; Ex. 2; Cn. 1	Slight crack	Bottom packed dry, top moist.
6	"	"	D.	Cn. 4; Ex. 5	White crack	Packed with square smooth end, soft.
7	H. Clark	James	N	Cn. 11	Very slight crack	" rotary motion, dry.
8	"	"	C. O.	Cn. 2	Distinct crack	" rather dry.
9	G. A. Swann	Phillips	Q	Cn. 3; Ex. 1	"	Mortar, medium, dry, rotary.
10	"	Dawson	R	Cn. 4	"	8 months old, in hand, dry, rotary motion.
11	"	Burck	H	Cn. 5	"	" mortar and hand, very dry, rubbed in.
12	C. E. Parsons	Alba	O	Cn. 5; Ex. 3	Very slight crack	" soft, pieces.
13	"	"	X	Cn. 5; Ex. 3	Wide crack	Instrument heated, surplus carried off by gold
14	Capon	Splendid	G	Cn. 4; Ex. 4; Cn. 1	Marginal not good.	Cut June 21st, 1896, became loose in tube.
15	"	Half Splendid, half James	A. J.	Cn. 4; Ex. 1	Wide crack	Same ingot, fresh cut, not annealed.
16	H. J. Kead	Globe	C. E.	Cn. 4; Ex. 1	Slight crack half-way around	" and annealed.
17	"	Same ingot.	S	Cn. 9	Wide crack all around.	"
18	"	"	A. R.	Cn. 8; Ex. 1	"	Mortar and hand, rotary, slight excess.
19	A. J. McIlough	Furka	A. G.	Cn. 5; Ex. 1	"	" packed vertically, no excess.
20	"	Dawson's White	C. G.	Cn. 5; Ex. 1	"	"
21	"	Burck	A. H.	Cn. 1; Ex. 1	Slight crack	Fresh, not annealed.
22	C. H. Waldron	James	F	Cn. 1; Ex. 1	"	Same as above, surplus removed with dry filings.
23	"	"	T	Cn. 2; Ex. 1	"	"
24	"	"	A. A.	Cn. 6	Wide	" in F.
25	"	Recovered from scraps.	I	Cn. 2; Ex. 3	Marginal broken	Three weeks old, very wet.
26	J. F. Adams	James	W	Ex. 1	Very slight crack	Six months old, not annealed.
27	"	"	P	Ex. 1	Above all around	Re-annealed twenty minutes in boiling water.
28	F. D. Price	Price's	A. Z.	Ex. 6	Marginal broken	Packed dry, rubbed in.
29	F. B. Noyes	Sterling Redund	C	Ex. 1	Distinct crack	Mortar and hand, packed moist.
30	A. E. Parker	Alba (3 weeks old)	K	Cn. 1; Ex. 1	Very slight crack	" dry as possible, surplus removed with dry filings.
31	W. C. Trotter	Melican White (1 month)	A. F.	Cn. 2; Ex. 3	Slight crack	" and hand.
32	H. E. Eaton	Dawson's White	E	Cn. 2; Ex. 3	Distinct crack	Old hard pieces mixed with it. Pieces size of small
33	G. S. Martin	Splendid (3 months)	A. B.	Cn. 6	"	wheat grain; surplus rubbed off with chamois.
34	F. J. Ross	"	T	Cn. 6	"	"

* This formula must be incorrect.

Note—Cn. Contraction; Ex. Expansion; Point, one ten-thousandth of an inch.