JORDAN PETROLEUM REFINERY CO. LTD.

LABORATORY

Certificate No. :
Date Issued :
Tank No. :
Sampling Date :

SPECIFICATION

Asphalt
80/100

TESTS		RESULTS		METHODS
Ductility @ 25 °C.	cm	100	Min.	ASTM D-113
Penetration @ 25 °C.	0.1 mm	80 -	100	ASTM D-5
Softening Point,	°C	45.8 -	48	ASTM D-36
Specific Gravity @ 25°/25°C		1.0	Min.	ASTM D-70
Loss on Heating to 163°C	%wt.	1.0	Max.	ASTM D-6
Penetration of residue from loss on heating test at 25°C as compared to penetration before heating	%	75	Min.	ASTM D-5
Solubility in Trichloroethylene,	%wt.	99.5	Min.	ASTM D-2042
Ash Content,	%wt.	1.0	Max.	ASTM D-482
Flash point (Cleveland Open Cup), °C		225	Min.	ASTM D-92

Remarks :

(Lab.) Chief Chemist