

Samples of White Lead in Oil—Continued.

RESULTS OF ANALYSIS.				No. of Sample.	Remarks of Official Analyst.
Lead Oxide.	Carbon Dioxide.	Barium Sulphate.	Oil.		
p. c.	p. c.	p. c.	p. c.		
79.16	12.08	7.56	19471	Unadulterated.
76.52	11.73	10.58	19472	"
79.31	12.94	6.84	19473	"
79.37	12.30	7.08	19474	"
71.96	12.08	7.96	8.00	19475	Adulterated with sulphate of barium.
78.93	12.86	7.34	19476	Unadulterated.
79.17	11.25	8.31	19477	"
78.87	12.40	7.30	19479	"
65.76	9.57	17.42	6.28	19480	Adulterated with barium sulphate.
49.48	7.71	31.45	9.60	19481	" "
69.54	10.21	7.02	10.56	19482	" "
77.71	11.42	8.69	17310	Genuine.
26.92	3.63	58.50	7.91	17311	Adulterated.
80.50	11.49	5.63	17312	Genuine.
78.32	11.37	8.45	17313	"
51.50	6.56	21.92	8.77	17314	Adulterated.
66.34	9.10	13.36	7.72	17315	"
77.13	10.02	7.97	17316	Genuine.
78.38	11.69	7.81	17317	"
23.31	3.10	60.25	10.28	17318	Adulterated.
76.53	11.30	10.10	17319	Genuine.