

WHITE LEAD (GROUND IN OIL).

Inspector's Report (Is not an expression of opinion).	Results of Analysis.				No. of Sample.	Remarks and Opinion of the Chief Analyst.
	Sample.		Pigment.			
	Vehicle (Oil)	Solids (Pigment).	Lead soluble in acetic acid estimated as basic carbon- ate.	Residue Insol- uble to Acetic Acid.		

H. J. DAGER, INSPECTOR.

	p. c.	p. c.	p. c.	p. c.			
Egyptian White Lead.	8.6	91.4	13.30	Zinc sulphide = 61.02%	Zinc oxide = 9.90%	62195	Contains barytes, without declaration.
Diamond White Lead, guaranteed strictly pure.	6.7	93.3	98.73	5.32		62197	Genuine.
London White Lead.	7.1	92.9	43.25	55.80		62198	Contains barytes, without declaration.
.....	7.7	92.3	26.60	72.76		62199	Chiefly barytes, without declaration.
.....	7.9	92.1	40.72	57.94		62200	Contains barytes, without declaration.

H. J. DAGER, ACTING INSPECTOR.

.....	6.5	93.5	53.93	42.93		63282	Contains barytes, without declaration.
London White lead..	7.4	92.6	42.67	56.72		63284	" "
.....	7.5	92.5	27.97	70.84		63285	" "
Green Seal White Lead.	7.0	93.0	98.46	0.84		63286	Genuine.
Colonial White,....	7.5	92.5	21.64	75.56		63287	Contains barytes, Lead not claimed.

JNO. TALBOT, INSPECTOR.

Labelled "White Lead".	7.3	92.7	45.86	41.96	Zinc Oxide = 9.78%	53678	Contains barytes, without declaration.
Labelled American White, ground in pure Linseed Oil.	10.3	89.7	None....	Barite = 82.98% % Zinc sulphide = 13.20%		53680	Contains no Lead. Not sold as Lead.
.....	7.3	92.7	49.68	45.92		63908	Contains barytes, without declaration.
Labelled, White Lead, ground in pure Linseed Oil.	9.0	91.0	None....	Barite = 92.62% % Zinc sulphide = 7.03%		63909	Contains no Lead.
Labelled, White Lead, warranted ground in refined Linseed Oil.	8.6	91.4	56.33	40.40		63911	Contains barytes without declaration.