

Amherst Stone.

Brighter in color and coarser in grain than the Sackville.
Cement is clay and oxide of iron.

Specific Gravity	2.7
Weight per cubic foot	142.93
Pore Space	15.20
Ratio of Absorption	6.894
Coefficient of Saturation, 1 hour	.47
Coefficient of Saturation, 2 hours	.59
Crushing Strength	11122.
Crushing Strength, wet	6938.
Crushing Strength, wet, after freezing	4000.
Loss on Corrosion	.00454
Transverse Strength	551.
Chiselling Factor	4.8
Drilling Factor	19.5
Ferrous Oxide	1.8
Ferrie Oxide	3.71



Residence, Deancroft, Glen Road, New Brunswick Sandstone.