

rings, and grub or large worm holes; but small worm holes and shakes shall be allowed, according to the judgment of the Culler. **SECOND QUALITY** shall be oak not coming within the definition of first quality, and which, in the judgment of the Culler, is not culls.

*Rock Elm.*

**SQUARE HARD GREY or ROCK ELM** shall be free from rots, open rings and rotten knots (affecting the surrounding wood); but shakes and slivers shall be allowed, according to the judgment of the Culler.

*White or Yellow Pine Timber.*

**SQUARE WHITE or YELLOW PINE TIMBER** shall be free from rot, rotten knots (affecting the surrounding wood), worm holes, open shakes and open rings; but sound knots shall be allowed, according to the judgment of the Culler.

*Square Red Pine Timber.*

**SQUARE RED PINE TIMBER** shall be free from rots rotten knots (affecting the surrounding wood), worm holes, shakes and splits; but sound knots shall be allowed, according to the judgment of the Culler.

*Square Ash, Basswood, and Butternut.*

**SQUARE ASH BASSWOOD and BUTTERNUT** shall be of the same quality as white or yellow pine square timber.

*Square Birch.*

**SQUARE BIRCH** shall be free from rot, rotten knots, splits, and shakes, and shall be allowed two inches wane.

*Masts, Bowsprits, and Red Pine Spars.*

**MASTS, BOWSPRITS, and RED PINE SPARS** shall be sound, free from bad knots, rents and shakes; and the heart shall be visible in spots at or near the partners.