




Map of Cuba.

The following table of analyses is taken from Fermor's report.<sup>2</sup>

TABLE No. 5  
Analyses of Lateritic Manganese Ores

|                  | Belgaum   | SHIMOGA           |                  | Sandur      |
|------------------|-----------|-------------------|------------------|-------------|
|                  |           | Higher grade ores | Lower grade ores |             |
| Manganese .....  | 31.2-60.8 | 44-56             | 30-38            | 39.47-54.29 |
| Iron .....       | 0.1-18.4  | 2-10              | 10-20            | 5.38-19.40  |
| Silica .....     | 0.6-2.5   | 1-3               | 2-6              | 0.43-1.00   |
| Phosphorus ..... | 0.01-0.12 | 0.015-0.600       | 0.01-0.6         | 6.016-0.033 |

<sup>2</sup> Ibid., p. 389.