

## WHITE PAINT.—

| Results of Analysis. |      |        |          |          |                                    |                                           |               |        | No. of Sample. | Remarks and Opinion<br>of the<br>Chief Analyst. |
|----------------------|------|--------|----------|----------|------------------------------------|-------------------------------------------|---------------|--------|----------------|-------------------------------------------------|
| Weight in Ounces.    |      |        | Vehicle. | Pigment. | Analysis of separated dry pigment. |                                           |               |        |                |                                                 |
| Total.               | Tin. | Paint. |          |          | Loss on<br>Ignition.               | Residue Insol-<br>uble in Nitric<br>Acid. | Lead (metal). | Found. |                |                                                 |

## F. X. W. E. BELAND, INSPECTOR.

| See   | No. | 5     | p. c. | p. c. | p. c. | p. c. | Aluminum |                   |         |       |                   |
|-------|-----|-------|-------|-------|-------|-------|----------|-------------------|---------|-------|-------------------|
| 17.3  | 2 2 | 15 1  | 31.5  | 68.5  | 6.71  | 38.59 | 15.28    | Zinc.             | Barium. | 56261 | Chiefly barytes.  |
| See   | No. | 63435 |       |       |       |       |          |                   |         | 56262 | Lead and barytes. |
| 16.85 | 2 4 | 14.45 | 30.1  | 69.9  | 5.00  | 46.28 | 15.47    | Zinc.             | Barium. | 56263 | " "               |
| 18.30 | 2 7 | 15.6  | 42.3  | 57.7  | 0.93  | 58.18 | 6.54     | Zinc and Aluminum | "       | 56264 | " "               |
|       |     |       |       |       |       |       |          |                   |         | 56265 | Chiefly barytes.  |

## ALP. PELLETIER AND F. X. ROY, TEMPORARY INSPECTORS.

|      |      |       |      |      |      |       |      |                    |         |       |                  |
|------|------|-------|------|------|------|-------|------|--------------------|---------|-------|------------------|
| 19.0 | 2.5  | 16.5  | 39.7 | 60.3 | 5.06 | 47.19 | 9.21 | Zinc.              | Barium. | 53393 | Chiefly barytes. |
| 16.7 | 2.25 | 14.45 | 39.0 | 61.0 | 2.11 | 54.91 | 6.85 | Zinc and aluminum. | "       | 2003  | "                |
| 16.0 | 2.75 | 13.25 | 55.0 | 45.0 | 8.22 | 59.06 | 1.80 | Zinc.              | "       | 2010  | "                |
| 16.0 | 2.4  | 13.6  | 42.3 | 57.7 | 2.06 | 52.16 | 8.21 | "                  | "       | 2017  | "                |

## N. CADIEUX AND D. BROCHU, TEMPORARY INSPECTORS.

|      |     |       |      |      |      |       |      |       |         |      |                           |
|------|-----|-------|------|------|------|-------|------|-------|---------|------|---------------------------|
| See  | No. | 53393 |      |      |      |       |      |       |         | 2344 | Chiefly barytes.          |
| See  | No. | 61519 |      |      |      |       |      |       |         | 2345 | Essentially zinc oxide.   |
| 24.0 | 2.9 | 21.1  | 26.3 | 73.7 | 2.61 | 53.51 | 2.38 | Zinc. | Silica. | 2367 | Chiefly barytes.          |
| See  | No. | 62339 |      |      |      |       |      |       |         | 2382 | Essentially white lead.   |
| 19.0 | 2.4 | 16.6  | 30.4 | 69.6 | 5.64 | 37.14 | 2.43 | Zinc. | Barium. | 2537 | Chiefly barytes and zinc. |
| See  | No. | 53393 |      |      |      |       |      |       |         | 2542 | Chiefly barytes.          |