

RAW LINSEED OIL.

Inspector's Report. (Is not an expression of opinion.)	Results of Analysis.							Remarks and Opinion of the Chief Analyst
	Refractive Index at 25° C.	Sp. Gr. at 15.5° C.	Saponification Number.	Spot Test.	Unsatifiable Matter.	Iodine Number (Hanus).	Time of Drying at 70° C.	

D. O'SULLIVAN, INSPECTOR.

.....	1.4800	0.9342	190.0	185.0	19 hrs.	66789	Genuine.
.....	1.4792	0.9324	189.0	178.0	19 "	66791	"
.....	1.4802	0.9342	189.0	182.0	19 "	66794	"
.....	1.4802	0.9343	189.0	183.0	19 "	66796	"
.....	1.4800	0.9338	189.0	185.0	19 "	66798	"
.....	1.4800	0.9339	189.0	185.0	19 "	66800	"
.....	1.4800	0.9335	190.0	186.0	19 "	66602	"
.....	1.4805	0.9342	189.0	189.0	19 "	66604	"

No. 332—

Furnisher
endor.

Furnisher

VICTORIA—

J. Begg, Ltd.,
 Vancouver.
 J. B. Bell & Co.,
 London, Eng.
 A. Paint Co.,
 Victoria.
 " "
 Erwin-Wil-
 liams, Winni-
 peg.
 A. Paint Co.,
 Victoria.
 Alberta Linseed
 Oil Mills, Medi-
 cine Hat.
 Ramsay &
 Co., Montreal.