ASSAYS BY DR. B. J. HARRINGTON.

3.

In the foregoing Report nothing is said with regard to gold localities outside of Marmora; but a few specimens from the Townships of Levant and Elzevir having been examined at the same time as those from Marmora, it has been thought advisable to include the results in the following table. In most cases silver was absent, or, if present, occurred in such minute quantity as to be of no economic value :--

Names of Mines or of Proprietors.	Township, Lot and Rauge.	Character of Gre	of Gold per ton 2000 lbs	Value per ton. (2000 lbs.)	
Gillen Miue	Marmora, 6, 8.	{ Mispickel and quartz }	4.90	\$101 23	A vein worked at present
		Mispickel and quartz }	0.6125	12 65	Not from the same vein as the above.
Gatling Mine	.4 9, 8.	" (Ordinary and)	3.736 No	77 18	Now being worked.
Williams & Co.		rites with chloriticmat-	trace of gold or silver.		Occurs in magnetic iron in the vicinity of the Marsl Ore Bed.
	et (1	(Finely gran-)	41		This, like the last, was a surface specimen, no openings having been
Cooke or Wil- } liams' Mine. }		Mispickel and vitreous quartz	4 14	85 53	made. Worked at present.
а а та	ec 46	tailings form Dr. Williams' Mill, chiefly quartz and mispickel	0.8458	17 47	Trials on a large scale are said to have yielded a much larger amount o gold; bu' the quantity o course varies according to the degree to whiel
(1	٤. ٤.	Similar to the last but not so well con- centrated	0.460	9 71	the tailings have been concentrated.
Williams, } Deau & Co. }	" 20 5	Mignickal	1.545	31 92	From a locality not ye described, and belong ing apparently to a dit ferent horizon from any of the above.
B. Hutchins, } Esq	Levant, 6, 7	White quartz with chlorite and copper pyrites	No goldor silve r .		Some years ago a few small openings wer- made on this and the following lots for cop- per.
cc 66	" 4 or 5, 7	. Fahlband	Trace of gold	i	1
		Compact quartzose do- lomite, hold- ing sulphides of iron and copper	0.255	5 27	