

JORDAN PETROLEUM REFINERY CO. LTD.
LABORATORY

Certificate No. _____
Date Issued _____
Tank No. _____
Sampling Date _____

SPECIFICATION
Liquid Asphalt
MC - 70

TESTS	RESULTS	METHODS
Viscosity :		
Kinematic @ 140°F, cSt	70 - 140	ASTM D-3170
Saybolt Furol @ 122°F, Sec.	60 - 120	ASTM D-88
Flash Point (Tag Open - cup), °F	100 Min.	ASTM D-1810
Distillation test :		ASTM D-402
Distillate, Percent by volume of total distillate to 360 °C		
to 221 °C	20 Max.	
to 300 °C	20 - 60	
to 316 °C	65 - 90	
Residue from distillation to 360 °C, Percent volume by difference	55 Min.	
Test ex residue from distillation :		
Penetration @ 25 °C, 100 gm, 5 sec.	120 - 250	ASTM D-5
Ductility @ 25 °C cm	100 Min.	ASTM D-113
Solubility in trichlorobenzene, Percent	9.2 Min.	ASTM D-2042
Water, Percent	0.2 Max.	ASTM D-95

Remarks : _____

(Lab.) Chief Chemist

W. J. ...
3/1/44