

TABLE VIII.

Average Value of Gold per oz., Troy.

FINENESS IN CARATS.	\$	£	s.	d.
24	20.65	4	5	0
22	18.93	3	17	11
20	17.21	3	10	10
18	15.49	3	3	9
16	13.77	2	16	8
14	12.05	2	9	7
12	10.32	2	2	6

NOTE—The value of silver is subject at present to constant fluctuation. The average Bar or Standard Silver will probably oscillate for some time at a few cents over \$1 per oz. Troy. Standard Silver consists of 92.5 % pure silver, and 7.5 % copper alloy. Cupelled or Cake Silver will average about a twelfth more in value.

TABLE IX.

Approximate Sp. Gr. of Gold Alloys.

FINENESS IN CARATS.	SP. GR.	GOLD, %.	ALLOY (CU-AG) %.
23	18.56	95.83	4.17
22	17.74	91.67	8.33
21	17.22	87.50	12.50
20	16.60	83.34	16.66
19	16.00	79.17	20.83
18	15.42	75.00	25.00
17	14.92	70.83	29.17
16	14.48	66.67	33.33
15	14.06	62.50	37.50
14	13.65	58.33	41.67
13	13.28	54.17	45.83
12	12.91	50.00	50.00