

PART 7 - TEST FOR VERTICALLY SUPPORTED TEXTILES AND FILMS

1 Application

Where draperies, curtains and other supported textile materials are required to have qualities of resistance to the propagation of flame not inferior to those of wool of mass 0.8 kg/m^2 , they shall comply with this part.

2 Fire test procedure

The vertically supported textiles and films shall be tested and evaluated in accordance with the fire test procedure specified in resolution A.471(XII) as amended by resolution A.563(14).

3 Additional requirements

The tests shall be made by using specimens of the final product (e.g. with colour treatment). In cases where only the colours change, a new test is not necessary. However, in cases where the basis product or the treatment procedure change, a new test is required.