

JORDAN PETROLEUM SERVICES CO. LTD.

LABORATORY

Customer's No.: _____
 Date Issued: _____
 Order No.: _____
 Sampling Date: _____

SPECIFICATION

Liquid Asphalt
 PC - 250

TESTS	RESULTS	METHODS
Viscosity :		
Kinematic @140F, cSt	250 - 500	ASTM D-1170
Saybolt Furol @140F, Sec	125 - 250	ASTM D-88
Flash Point (Tag Open-cup), °F	Min. - Max.	ASTM D-1810
Distillation test :		ASTM D-402
Distillate, Percent by volume of total distillate to 300 °C		
to 225 °C	35 Min.	
to 260 °C	60 Min.	
to 316 °C	80 Min.	
Residue from distillation to 360 °C,		
Percent volume by difference:	65 Min.	
Test on residue from distillation :		
Penetration @ 25 °C 100 gm 5mm	100 Min.	ASTM D-113
ductility @ 25 °C cm	99 Min.	ASTM D-2042
Solubility in trichloroethylene, Percent	0.2 Max.	ASTM D-95
Water, Percent		

Remarks :

(Lab.) Chief Chemist

Muzel

21.1.94