

TABLE B.2.2 GENERAL DESCRIPTION OF NON-FERROUS SMELTER CONTAINMENT - SO₂

Smelter	Location	Sulphur Containment Process	SO ₂ Containment	% ¹
Hudson Bay Mining and Smelting Co. Limited	Flin Flon, Manitoba	None installed	Nil	
INCO Limited	Thompson, Manitoba	None installed	Nil	
INCO Limited	Copper Cliff, Ontario	Liquid sulphur dioxide produced from copper flash furnace in copper-nickel smelter	365 tonnes per day	11
INCO Limited	Copper Cliff, Ontario	Sulphuric acid produced in contact acid plants from the iron ore recovery plant	1600 tonnes per day	85
Falconbridge Nickel Mines Limited	Sudbury, Ontario	Sulphuric acid produced in contact acid plant from fluid-bed roasters	525 tonnes per day	65
Noranda Mines Limited, Horne Division	Noranda Québec	None installed	Nil	
Noranda Mines Limited, Gaspé Division	Murdochville Québec	Sulphuric acid produced in contact acid plant from fluid-bed roasters	330 tonnes per day	60

¹ Percent SO₂ contained (sulphur contained to total sulphur input)