

ELECTRIC STEEL REFINING.

By D. F. CAMPBELL (London).

(Paper read before the Iron and Steel Institute.)

The use of electricity for the refining of steel has now taken its place amongst established metallurgical processes, and many papers have been written on the subject of electric furnaces, but the author proposes to discuss briefly the general aspects of the subject, and what he considers the probable and possible developments in the immediate future in England. The electric furnace is at present used in various works for the refining of steel from the Bessemer converter in the manufacture of rails and all classes of railway material and castings, and more commonly in connection with the basic open-hearth process for the manufacture of various products of intermediate quality, castings and tool steel of all kinds. These are the purposes for which it has been most widely adopted, notably in America, Germany and France, although it is also used for melting and refining charges of cold scrap of cheap quality for the manufacture of tool steel and small castings, and its high efficiency is now generally acknowledged. The refining of steel that had been previously melted was the first use to which the electric furnace was applied commercially; but now that single furnaces have been producing over 200 tons a day for more than sixteen months, it is obvious that the field for the process has widened, and already many furnaces are in construction or operation in this country.

The author is of opinion that the electric furnace is especially suitable, and will be widely adopted, for any class of work in which raw materials of a high degree of purity are now used.

A wider application for rails and sections may occur when working in connection with the Talbot furnace, for the charge can be taken to the electric furnace as soon as the carbon is down, and the necessity of removing the sulphur and getting a teeming heat is avoided, as this is done in the electric furnace both economically and completely. Thus the capacity of the Talbot furnace is substantially increased, and this covers the greater cost of electric refining.

Again, in the case of a basic open-hearth plant, using 60 per cent. of molten pig iron and 40 per cent. of scrap, a 40-ton furnace might have 15 tons removed to the electric furnace for refining, and a similar charge put in every two hours. Thus the capacity would be increased, the quality improved, and, in addition, a reduction in the cost of raw materials can also be made in some cases, as a low quality of pig iron can be used.

Similar conditions occur when working in conjunction with an open-hearth plant for making castings, and a thoroughly dead melt and extreme fluidity can be obtained, while the commonest raw materials can be used, and refined completely. This gives economy both in the amount of gits and runners, and also in the reduction of wasters. Even in the case of foundries engaged in ordinary open-hearth casting work, in which the margin of profit is now exceedingly small, the electric furnace is considered necessary for an improvement in quality, while in a small foundry making light and intricate castings from crucible steel, an economy of several pounds per ton may be expected to result from the adoption of the electric furnace, judging from the reduction of the costs in works in Germany where crucible furnaces were replaced by this process.

There is little doubt that crucible steel, Swedish billets and products of intermediate quality, such as are used for the Sheffield trade and by tubemakers of Staffordshire and South Wales, can be econo-

mically replaced by steel refined by electricity, and made in Middlesbrough, Cumberland, or the larger steel works in the Sheffield and Rotherham districts.

The use of the electric furnace is not likely to become general for rail steel manufacture at the present time, except in cases where the conditions are exceptional. In certain cases, such as at South Chicago, it has been adopted for that purpose owing to the economic conditions, notably the scarcity of good Bessemer ores and the demand for better rails. The electric furnace in such cases may save Bessemer plants from the scrap heap, or, at any rate, prolong the life of present installations, and at the same time make it possible to produce rails of a quality better than the best open-hearth steel, thus avoiding heavy capital expenditure.

In the electric furnace, almost any degree of refining can be economically effected, and the removal of sulphur, phosphorus, and oxygen is especially easy. This is probably due to at least three causes:

1. The intense heating of the slag, which is the place at which refining takes place. Owing to this high temperature and the extreme fluidity of the slag, the rate of the refining reaction is very great, because the velocity of reaction rises very quickly for high temperatures, and not in direct proportion to the temperature.

2. The extremely basic slag that can be kept in a very fluid state, and the calcium carbide formed by the action of the arc on the calcareous slag, are especially advantageous for desulphurization.

3. The violent motion of the steel, which results from the convection currents produced in the bath, due to the two intensely hot areas caused by the arc below the electrodes, increases the volume of steel exposed to the hot and fluid slag area, and hence the rate of refining.

The usual procedure for the use of the electric furnace in connection with the Bessemer converter is to charge the steel, holding back all slag in the ladle, after putting on the bottom of the furnace, lime and mill scale or iron ore. This produces an oxidizing or dephosphorizing slag, which may be carefully skimmed or poured off. On the bath of steel carbon is thrown to carburize to any required degree, and then a second highly basic and desulphurizing slag is added. The arc acting on the calcareous slag produces calcium carbide, which may combine with sulphur to form calcium sulphide. As neither gases nor air enter the furnace, and the conditions are almost completely reducing, no sulphates are formed, a dead melt is easily obtained, and when the slag is molten and the requisite heat obtained, the steel is teemed. In the open-hearth or any oxidizing furnace these reactions cannot take place so completely and efficiently.

With steel from the basic open-hearth furnace, the procedure is similar, but when the quantity of phosphorus to be removed is small, it is only necessary to use one refining slag for the elimination of sulphur and any small amount of phosphorus remaining. The usual practice is to put the carbon necessary for carburizing in the bottom of the furnace and then add the steel, and the basic slag materials. As soon as the teeming heat is obtained, the necessary ferro-alloys are added and the steel will be completely refined.

Another point of interest is the rarity of blow-holes in electric steel when properly made, and this leads to the question of the cause of these troubles. It is well known that any ingot of steel when placed in a vacuum evolves nitrogen, and this is about equally true whether it be made in the crucible, the Bessemer converter, or the electric furnace. Blow-holes contain nitrogen, but this is probably not the cause. It is far more probable