

TABLE No. 7

Oil Mixture—Ketone residue (F.P.L. No. 29)—25 per cent.
 Coal tar creosote 65 " "
 Coal tar 10 " "

Lb. of oil mixture per ton of dry ore—1.06.

| Date | Shift | Tons of ore treated | Assay oz. of silver per ton | | | | Per cent Extraction |
|-------------|------------|---------------------|-----------------------------|------------|-------------|----------------|---------------------|
| | | | Heads | Tails | Middlings | Concentrates | |
| May 7..... | 3-7 | 160 | 7.8 | 1.2 | 26.6 | 173.0 | 85.0 |
| May 8..... | 11-7 | 212 | 9.4 | 1.0 | 14.0 | 317.0 | 89.6 |
| May 9..... | 7-3 3-7 | 277 | 9.2 8.2 | 1.1 0.9 | 13.0 7.4 | 267.5 290.0 | 88.4 89.3 |
| May 10..... | 7-3 | 90 | 8.8 | 0.9 | 87.6 | 382.0 | 90.0 |