

**CIHM
Microfiche
Series
(Monographs)**

**ICMH
Collection de
microfiches
(monographies)**



Canadian Institute for Historical Microreproductions / Institut canadien de microreproductions historiques

© 1997

Technical and Bibliographic Notes / Notes techniques et bibliographiques

The Institute has attempted to obtain the best original copy available for filming. Features of this copy which may be bibliographically unique, which may alter any of the images in the reproduction, or which may significantly change the usual method of filming are checked below.

- ☒ Coloured covers / Couverture de couleur
- ☐ Covers damaged / Couverture endommagée
- ☐ Covers restored and/or laminated / Couverture restaurée et/ou pelliculée
- ☐ Cover title missing / Le titre de couverture manque
- ☐ Coloured maps / Cartes géographiques en couleur
- ☐ Coloured ink (i.e. other than blue or black) / Encre de couleur (i.e. autre que bleue ou noire)
- ☐ Coloured plates and/or illustrations / Planches et/ou illustrations en couleur
- ☐ Bound with other material / Relié avec d'autres documents
- ☐ Only edition available / Seule édition disponible
- ☐ Tight binding may cause shadows or distortion along interior margin / La reliure serrée peut causer de l'ombre ou de la distorsion le long de la marge intérieure.
- ☐ Blank leaves added during restorations may appear within the text. Whenever possible, these have been omitted from filming / Il se peut que certaines pages blanches ajoutées lors d'une restauration apparaissent dans le texte, mais, lorsque cela était possible, ces pages n'ont pas été filmées.
- ☐ Additional comments / Commentaires supplémentaires:

L'Institut a microfilmé le meilleur exemplaire qu'il lui a été possible de se procurer. Les détails de cet exemplaire qui sont peut-être uniques du point de vue bibliographique, qui peuvent modifier une image reproduite, ou qui peuvent exiger une modification dans la méthode normale de filmage sont indiqués ci-dessous.

- ☐ Coloured pages / Pages de couleur
- ☐ Pages damaged / Pages endommagées
- ☐ Pages restored and/or laminated / Pages restaurées et/ou pelliculées
- ☒ Pages discoloured, stained or foxed / Pages décolorées, tachetées ou piquées
- ☐ Pages detached / Pages détachées
- ☒ Showthrough / Transparence
- ☐ Quality of print varies / Qualité inégale de l'impression
- ☐ Includes supplementary material / Comprend du matériel supplémentaire
- ☐ Pages wholly or partially obscured by errata slips, tissues, etc., have been refilmed to ensure the best possible image / Les pages totalement ou partiellement obscurcies par un feuillet d'errata, une pelure, etc., ont été filmées à nouveau de façon à obtenir la meilleure image possible.
- ☐ Opposing pages with varying colouration or discolourations are filmed twice to ensure the best possible image / Les pages s'opposant ayant des colorations variables ou des décolorations sont filmées deux fois afin d'obtenir la meilleure image possible.

This item is filmed at the reduction ratio checked below / Ce document est filmé au taux de réduction indiqué ci-dessous.

10x		14x		18x		22x		26x		30x	
						☒					
	12x		16x		20x		24x		28x		32x

The copy filmed here has been reproduced thanks to the generosity of:


National Library of Canada

The images appearing here are the best quality possible considering the condition and legibility of the original copy and in keeping with the filming contract specifications.

Original copies in printed paper covers are filmed beginning with the front cover and ending on the last page with a printed or illustrated impression, or the back cover when appropriate. All other original copies are filmed beginning on the first page with a printed or illustrated impression, and ending on the last page with a printed or illustrated impression.

The last recorded frame on each microfiche shall contain the symbol $\longrightarrow$ (meaning "CONTINUED"), or the symbol ∇ (meaning "END"), whichever applies.

Maps, plates, charts, etc., may be filmed at different reduction ratios. Those too large to be entirely included in one exposure are filmed beginning in the upper left hand corner, left to right and top to bottom, as many frames as required. The following diagrams illustrate the method:



L'exemplaire filmé fut reproduit grâce à la générosité de:


Bibliothèque nationale du Canada

Les images suivantes ont été reproduites avec le plus grand soin, compte tenu de la condition et de la netteté de l'exemplaire filmé, et en conformité avec les conditions du contrat de filmage.


Les exemplaires originaux dont la couverture en papier est imprimée sont filmés en commençant par le premier plat et en terminant soit par la dernière page qui comporte une empreinte d'impression ou d'illustration, soit par le second plat, selon le cas. Tous les autres exemplaires originaux sont filmés en commençant par la première page qui comporte une empreinte d'impression ou d'illustration et en terminant par la dernière page qui comporte une telle empreinte.

Un des symboles suivants apparaîtra sur la dernière image de chaque microfiche, selon le cas: le symbole $\longrightarrow$ signifie "A SUIVRE", le symbole ∇ signifie "FIN".

Les cartes, planches, tableaux, etc., peuvent être filmés à des taux de réduction différents. Lorsque le document est trop grand pour être reproduit en un seul cliché, il est filmé à partir de l'angle supérieur gauche, de gauche à droite, et de haut en bas, en prenant le nombre d'images nécessaire. Les diagrammes suivants illustrent la méthode.



(ANSI and ISO TEST CHART No. 2)



APPLIED IMAGE Inc

1653 East Main Street
Rochester, New York 14609 USA
(716) 482 - 0300 - Phone
(716) 288 - 5989 - Fax

SECTIONS AND ANALYSES OF
NOVA SCOTIA COALS.

BY EDWIN GILPIN, JR., A. M., LL. D., F R. S. C.,
ETC., ETC.

*From the Transactions of the Nova Scotian Institute of Science,
Vol. XI., Session 1902-1903.*

SECTIONS AND ANALYSES OF NOVA SCOTIA COALS.—BY EDWIN
GILPIN, JR., A. M., LL. D., F. R. S. C., etc., etc.

(Read 18th May, 1901.)

I venture to submit the following sections and analyses of Nova Scotia coals. The paper refers only to seams which are at present being worked, and the sections and analyses have all been recently measured and made. While the true value of coals may be better determined by ultimate analyses and practical tests for coking, evaporative power, etc., these results may be of interest to the members of the Institute.

SECTIONS OF NOVA SCOTIA SEAMS.

PICTOU COUNTY.

*Intercolonial Coal Mining Company, Drummond Colliery
Westville :*

Main Seam, section taken 200 feet below No. 14 lift :

	Feet.	Inches.
<i>Top coal (course)</i>	2	2
<i>Full coal</i>	3	8
<i>Fire-clay</i>	0	5
<i>Top-ply coal</i>	2	0
<i>Bench coal</i>	5	2
<i>Stone</i>	0	5
<i>Bench coal</i>	2	8
<i>Stone</i>	0	5
<i>Bottom coal</i>	3	0
Total	19	11

Main Seam at No. 4 Slope, top level :

	Feet.	Inches.
<i>Coal (course)</i>	1	2
<i>Fire-clay</i>	0	5
<i>Coal</i>	3	6
<i>Pyritous parting</i>	0	1
<i>Coal</i>	2	10
Total	8	0

Acadia Coal Company:

Acadia Main Seam at south level sinking, Acadia Colliery, Westville:

	Feet.	Inches.
<i>Top coal</i>	9	10
<i>Fall coal</i>	3	6
<i>Soft carbonaceous shale</i>	0	3
<i>Coal</i>	4	4
<i>Coal (coarse)</i>	2	0
<i>Coal (bench)</i>	3	6
Total	14	5

Deep Seam, at No. 4 balance, 1900 feet level, Albion Mines, Stellarton:

	Feet.	Inches.
<i>Coal</i>	4	4
<i>Coal (coarse)</i>	3	8
<i>Coal</i>	12	0
Total	20	0

Third Seam, south level, 2000 feet from slope, Albion Mines, Stellarton:

	Feet.	Inches.
<i>Coal</i>	9	0
<i>Coal (coarse)</i>	0	9
<i>Coal</i>	3	3
Total	13	0

McGregor Seam, Albion Mines, Stellarton:

	Feet.	Inches.
<i>Coal (Fleming Seam)</i>	4	2
<i>Coal, coarse, (parting)</i>	5	0
<i>Coal</i>	6	0
<i>Hard shale with ironstone nodules (not persistent)</i>	0	6
<i>Coal</i>	15	0
Total	30	8

Six Feet Seam, Vale Colliery, Thorburn :

This seam does not maintain a regular thickness, varying from 3 to 6 feet, within short distances. Thus in No. 1 balance, north side, it runs from $3\frac{1}{2}$ to 5 feet clean coal. In Nos. 2 and 3 balances, same district of the mine, it runs from 4 to $6\frac{1}{2}$ feet of good coal. In the sinking it shows from 6 to 7 feet of good coal.

Nova Scotia Steel and Coal Company :

G. Mackay Seam, Marsh Colliery :

	Feet.	Inches.
Coal (coarse).....	0	1
Coal	3	0
Coal (coarse).....	0	4
Stone	0	1
Coal	0	4
Total	3	10

CUMBERLAND COUNTY.

Cumberland Railway and Coal Company, Springhill :

No. 2 (or West) Slope :

	Feet.	Inches.
West Seam,—west side	8	0
Aberdeen Seam (extension of West Seam)	8	0
Under Seam, { (split extension of Middle	4	0
Over Seam, { [or East] Seam)..	4	0

No. 3 (or North) Slope :

North Seam,—west side.....	8	3
North Seam,—east side	4	0

II SECTIONS AND ANALYSES OF N. S. COALS. — GILPIN.

Canada Coals and Railway Company, Joggins :

	Feet.	Inches.
Coal	3	0
Clay	1	2
Coal	1	6
Total	5	8

Minudie Coal Company, Minudie Colliery, River Hebert :

	Feet.	Inches.
Coal	1	7
Fireclay	0	2
Coal	1	9
Total	4	0

Stratheona Coal Company, Stratheona Colliery, River Hebert :

Milner Seam (?) :

	Feet.	Inches.
Coal (with parting)	2	6

Jubilee Colliery, Maccan River.

Coal	2	0
------------	---	---

Maritime Coal Company, Chignecto Colliery, Maccan :

	Feet.	Inches.
Coal	2	6
Fire-clay	1	6
Coal (with parting)	5	6
Total	9	6

CAPE BRETON COUNTY.

Gowrie and Blockhouse Collieries, Port Morien :

Gowrie Seam :

	Feet.	Inches.
Coal	4	10

Nova Scotia Steel and Coal Company, Sydney Mines :

Main (or No. 1) Seam at Princess Pit :

	Feet.	Inches.
Coal	5	4

Lloyd's Cove (or No. 2) Seam :

	Feet.	Inches.
Coal	2	3
Clay	0	2
Coal	0	6
Clay	0	0½
Coal	1	3½
Total	3	3

Main (or No. 3) Seam at Sydney Pond :

Coal	4	7½
----------------	---	----

Sydney Coal Company, North Sydney Colliery, Indian Cove

No. 3 (or Indian Cove) Seam :

	Feet.	Inches.
Splint coal	0	3
Coal	4	3
Total	4	6

Dominion Coal Company :

Phalen Seam at Caledonia Colliery, Glace Bay :

	Feet.	Inches.
Splint	0	0½
Coal	5	11½
Parting	0	0
Coal	1	6
Total	7	6

Phalen Seam, at Dominion No. 2 Colliery :

	Feet.	Inches.
Coal	7	6

13 SECTIONS AND ANALYSES OF N. S. COALS,—GILPIN.

Phalen Seam, at Dominion No. 3 Colliery :

<i>Coal</i>	5	3
<i>Splint</i>	0	0½
<i>Coal</i>	3	0
Total	8	3½

Phalen Seam, at Reserve Colliery :

	Feet.	Inches.
<i>Coal</i>	8	0

Phalen Seam, at Dominion No. 1 Colliery :

	Feet.	Inches
<i>Coal</i>	8	0

Harbor Seam, at Dominion No. 2 Colliery :

	Feet.	Inches.
<i>Splint</i>	0	1
<i>Coal</i>	6	5
Total	6	6

Harbor Seam, at International Colliery :

<i>Splint</i>	0	1
<i>Coal</i>	5	8
Total ..	5	9

VICTORIA COUNTY.

Cape Breton Coal Mining Company, New Campbellton :

Main Seam :

	Feet.	Inches
<i>Splint</i>	0	4
<i>Coal</i>	4	0
Total	4	4

INVERNESS COUNTY.

Inverness Railway and Coal Company, Broad Cove :

Seven Feet Seam :		
	Feet.	Inches.
<i>Coarse coal</i>	0	7
<i>Splint</i>	0	4
<i>Coal</i>	6	1
Total	7	0

Port Hood Coal Company, Port Hood :

Main Seam :		
	Feet.	Inches.
<i>Splint</i>	0	2
<i>Coal</i>	6	8
<i>Splint</i>	0	2
Total	7	0

Mabou Coal Mining Company, Mabou :

No. 1 (or Seven Feet) Seam :		
	Feet.	Inches.
<i>Coal</i>	1	6
<i>Shale parting</i>	0	1
<i>Coal</i>	1	6
<i>Shale parting</i>	0	1
<i>Coal</i>	2	0
<i>Clay</i>	0	1
<i>Coal</i>	1	9
Total	7	0

No. 2 (or Eight Feet) Seam :		
	Feet.	Inches.
<i>Shaley Coal</i>	1	0
<i>Coal with shale</i>	1	5
<i>Clay parting</i>	0	2
<i>Coal and shale</i>	0	6
<i>Soft fire-clay</i>	1	0
<i>Coal</i>	3	3
<i>Fre-clay</i>	0	3
<i>Coal, hard</i>	0	9
<i>Coal</i>	3	6
Total	11	10

15 SECTIONS AND ANALYSES OF N. S. COALS.—GILPIN.

No. 3 (or Fifteen Feet) Seam:

	Feet.	Inches.
<i>Shaley coal</i>	2	0
<i>Coal</i>	3	6
<i>Clay parting</i>	0	1
<i>Shaley coal</i>	0	6
<i>Coal</i>	2	6
<i>Shale parting</i>	0	2
<i>Coal</i>	1	3
<i>Shale parting</i>	0	1
<i>Coal</i>	4	0
Total	14	1

No. 4 Seam:

	Feet.	Inches.
<i>Coal</i>	2	6
<i>Canneloid coal</i>	1	6
<i>Coal</i>	2	0
Total	6	0

ANALYSES OF NOVA SCOTIA COALS.

PICTOR COUNTY.

	Volatile combustible matter.	Fixed carbon.	Ash.	Sulphur.	Mois- ture.
Interecolonial Main Seam..	25.73	65.36	8.20	1.10	.72
Marsh Colliery	35.43	55.48	9.99	1.26	..
Vale Colliery	28.80	55.30	14.50	.92	1.40
Acadia, Westville	28.09	60.77	9.99	1.24	1.15
McGregor Seam	28.37	61.13	10.50	1.43	*
Cage Pit Seam	29.88	59.34	10.78	.87	*
Third Seam	30.69	53.51	15.97	1.37	*
Acadia Mines, average....	26.80	62.20	9.70	1.15	1.30

*Moisture included in volatile matter.

SECTIONS AND ANALYSES OF N. S. COALS.—GILPIN. 16

CUMBERLAND COUNTY.

	Volatile combustible matter.	Fixed carbon.	Ash.	Sulphur.	Mois- ture.
Joggins	40.89	48.33	10.78	5.72	..
Minudie	36.15	52.45	9.60	5.04	1.80
Strathcona	37.36	52.25	10.39	4.47	..
Chignecto	39.75	48.75	9.95	6.02	1.55

Springhill (straight in levels):

No. 2 Slope, east side...	34.09	59.25	6.66	1.14	..
" " Minto Seam..	37.44	56.85	5.71	2.36	..
" " Aberdeen, east	32.30	60.49	7.31	1.02	..
" " " west	31.08	58.30	10.62	2.62	..
No. 3 Slope, west, 3800 ft.	35.36	59.72	4.92	.96	..
" " 2600 ft.	33.42	58.58	8.00	1.12	..
" " east, top, }					..
" " 2600 ft. }	36.44	58.54	5.02	1.10	..
" " east, top, }					..
" " 2600 ft. }	36.05	57.38	6.57	2.38	..
Average analysis Spring- hill coal.....	34.51	58.64	6.85	1.59	..

CAPE BRETON COUNTY.

Sydney Mines Main Seam...	36.27	57.05	4.76	2.01	1.92
Lloyd's Cove Seam	36.11	57.25	2.83	3.14	3.81
Lingan Main Seam	34.05	59.97	3.68	1.71	2.32

Phalen Seam:

Dominion No. 1	31.25	60.75	6.95	1.88	1.05
" No. 2	32.45	61.45	5.25	1.99	.85
" No. 3	31.65	62.20	5.00	1.67	.95
Caledonia ..	30.85	62.05	6.40	2.32	.70
Reserve.....	30.75	63.70	4.65	1.81	.90
Harbor Seam, at Inter- national.....	37.20	56.90	5.10	3.11	.80
Gowrie Seam, at Gowrie } and Blockhouse Col. }	36.00	57.70	5.20	3.82	1.10

17 SECTIONS AND ANALYSES OF N. S. COALS.—GILPIN.

VICTORIA COUNTY.

	Volatile combustible matter.	Fixed carbon.	Ash.	Sulphur.	Mois- ture
New Campbellton Main Seam	35.50	51.55	8.95	5.50	4.00

INVERNESS COUNTY.

Port Hood Main Seam....	34.67	56.39	8.94	1.10	..
Mabou, 7 Feet Seam	35.90	53.30	8.70	1.88	2.10
" 8 " "	34.25	56.40	6.95	1.85	2.40
" 15 " "	37.50	51.20	9.05	5.77	2.25
" 5 " "	35.65	49.55	11.95	5.20	2.85
" Average of seams	35.82	52.61	9.16	3.67	2.40
Broad Cove, 7 Feet Seam....	45.55	47.09	7.36	4.91	..

