CIHM Microfiche Series (Monographs) ICMH Collection de microfiches (monographies)



Canadian Institute for Historical Microreproductions / Institut canadien de microreproductions historiques



Technical and Bibliographic Notes / Notes techniques et bibliographiques

L'Institut a microfilmé le meilleur exemplaire qu'il lui a

été possible de se procurer. Les détails de cet exem-

plaire qui sont peut-être uniques du point de vue bibli-

ographique, qui peuvent modifier une image reproduite,

ou qui peuvent exiger une modification dans la métho-

de normale de filmage sont indiqués ci-dessous.

The Institute has attempted to obtain the best original copy available for filming. Features of this copy which may be bibliographically unique, which may alter any of the images in the reproduction, or which may significantly change the usual method of filming are checked below.

	Coloured covers /		Coloured pages / Pages de couleur
	Couverture de couleur		Pages damaged / Pages endommagées
	Covers damaged /		
	Couverture endommagée		Pages restored and/or laminated / Pages restaurées et/ou pelliculées
	Covers restored and/or laminated /		
	Couverture restaurée et/ou pelliculée		Pages discoloured, stained or foxed / Pages décolorées, tachetées ou piquées
	Cover title missing / Le titre de couverture manque		Pages detached / Pages détachées
	Coloured mans / Cartes déographiques en couleur		r ageo dotached / r ageo dotachedo
	Coloured ink (i.e. other than him ex black) (\square	Showthrough / Transparence
	Coloured Ink (i.e. other than blue G black) /	_	Our life of a sint series of
	Encre de couleur (i.e. autre que bieue ou noire)		Quality of phnt varies /
			Qualité inégale de l'impression
	Coloured plates and/or illustrations /		
	Planches et/ou illustrations en couleur	Ē	Includes supplementary material / Comprend du matériel supplémentaire
	Bound with other material /		
	Relié avec d'autres documents		Pages wholly or partially obscured by errata slips, tissues, etc., have been refilmed to ensure the best
	Only edition available /		possible image / Les pages totalement ou
	Seule édition disponible		partiellement obscurcies par un feuillet d'errata, une
			pelure etc. ont été filmées à nouveau de facon à
7	Tight binding may cause shadows or distortion along		obtenir la meilleure image nossible
	interior margin / La reliure serrée peut causer de		osterin la monodio image possible.
	l'ombre ou de la distorsion le long de la marge		Opposing pages with varying colouration or
	intérieure		discolourations are filmed twice to ensure the best
			possible image. (Les pages s'appagent event des
	Blank leaves added during restorations may appear		possible image / Les pages s'opposant ayant des
	within the text. Whenever possible, these have been		filmées deux fois afin d'obtanir la mailleura image
	omitted from filming / Il so nout que cortaines pages		nonces deux lois ann d'oblenn la memeure image
	blanchen sigutéen lere d'une restauration		possible.
	bianches ajoutees fors d'une restauration		
	apparaissent dans le texte, mais, lorsque cela etalt		
	possible, ces pages n'ont pas ete filmees.		
	Additional comments (
	Auditional comments /		
	Commentaires supplementaires:		

This item is filmed at the reduction ratio checked below / Ce document est filmé au taux de réduction Indiqué cl-dessous.



The copy filmed here has been reproduced thanks to the generosity of:

National Library of Canada

The images appearing here are the best quality possible considering the condition and legibility of the original copy and in keeping with the filming contract specifications.

Original copies in printed paper covers are filmed beginning with the front cover and ending on the last page with a printed or illustrated impression, or the back cover when appropriate. All other original copies are filmed beginning on the first page with a printed or illustrated impression, and ending on the last page with a printed or illustrated impression.

The last recorded frame on each microfiche shall contain the symbol \longrightarrow (meaning "CON-TINUED"), or the symbol ∇ (meaning "END"), whichever applies.

Maps, plates, charts, etc., may be filmed at different reduction ratios. Those too large to be entirely included in one exposure are filmed beginning in the upper left hand corner, left to right and top to bottom, as many frames as required. The following diagrams illustrate the method:

100

L'exemplaire filmé fut reproduit grâce à la générosité de:

Bibliothèque nationale du Canada

Les images suivantes ont été reproduites avec le plus grand soin, compte tenu de la condition et de la netteté de l'axemplaire filmé, et en conformité avec les conditions du contrat de filmage.

Les exemplaires originaux dont la couverture en papier est imprimée sont filmés en commençant par le premier plat et en terminant soit par la dernière page qui comporte une empreinte d'impression ou d'illustration, soit par le second plat, salon le cas. Tous les autres exemplaires originaux sont filmés en commençant par la première page qui comporte une empreinte d'impression ou d'illustration et en terminant par la dernière page qui comporte une telle empreinte.

Un des symboles suivants apparaîtra sur la dernière image de chaque microfiche, selon le cas: le symbole → signifie "A SUIVRE", le symbole V signifie "FIN".

Les cartes, planches, tableaux, etc., pauvent être filmés à des taux de réduction différents. Lorsque le document est trop grand pour être reproduit en un seul cliché, il est filmé à partir de l'angle supérieur gauche, de gauche à droite, et de haut en bas, en prenant le nombre d'images nécessaire. Les diagrammes suivants illustrent la méthode.





1	2	3
4	5	6

MICROCOPY RESOLUTION TEST CHART

(ANSI and ISO TEST CHART No 2)





1653 Lost Main Uree* Rochester New York 14609 USA (7161487 U300 Phone (716) 288 ~ 5989 Fax



1

14

5

National Library Bibliothèque nationale du Canada

.

÷.,

592

A. M. Bampbell

TRANSACTION OF THE CANADIAN MINING INSTITUTE. PART OF VOL. XXII.

Nubject to Revision. All publication rights reserved. AN INVESTIGATION OF CERTAIN CANADIAN PLATINUM AND MANGANESE RESOURCES.* BY G. C. MACKENZIE.

Annual Meeting, Montreal, March 5-7, 1919.

Prior to the war the world's supply of platinum was derived almost entirely from the Russian Urals, and when hostilities commenced in the fall of 1914 the Russian production was reduced almost one-third, due principally to the conscription of miners for the Russian army. This state of affairs was further aggravated by the fact that a very large quantity was required by the munition industries of England, France and the United States, in the manufacture of sulphuric acid, and also for the ignition apperatus of all types of internal combustion engines.

The State of Columbia, in Central America, is second only to Russia as an important source of platinum, producing in 1913, 15,000 onnees as against Russia's 250,000 onnees, whereas in 1916 Columbia produced 25,000 onnees, the Russian output falling to 63,900 onnees that year.

In 1906 platinum was worth from \$20 to \$38 per troy ounce; in 1914 its value increased to an average of \$45 per ounce. At the end of 1915 the price had again advanced to \$85 per ounce, and by December, 1916, had reached a figure of over \$100 per onnee. In the spring of 1918 the United States Government made an official fixed price of \$105 per ounce of refined platinum and adopted stringent regulations governing its purchase and exportation. The British Government followed suit in the fall of 1918 with the notion at they were prepared to pay the official American price for Canadian platinum.

The whole amount of platinum so far produced in the world to date is estimated by Dr. Geo. F. Kunz at 4,000,000 ounces, a quarter of which is assumed to be in the United States, with the addition of about 400,000 ounces of associated platinum metals.

He distributes this platinum in the various industries as follows :---

	U 2.
Catalyzing	400,000
Dental purposes	1,000,000
Chemical apparatus, etc.	1,000,000
Electrical devices	500,000
Jewellery	500,000

*By permission of Canadian Munition Resources Commission.

Kunz estimates also that the following amounts used for catalyzing purposes are distributed in the different countries about as follows:

United States	200.000
England	100,000
Germany	70,000
France	30,000
	400,000

The following table of the world's production is taken from Dr. Knnz's article in the Mineral Industry, Vol. XXV.: World's Production of New Platinum in 1913-1916, by Countries.

	(In trov o	ounces.)		
Country.	1913.	1914.	1915.	1916.
Ruscia, crude	(a)250.000	(a)241,200	(a) 124,000	(a)63,900
Canada, crude (b))50	(a)30	(a)100	(a)60
New South Wales and				
Tasmania, crude (c)	. 1,275	(a)1,248	303	222
Colombia, crude	(a) 15,000	(a)17,500	18,000	25,000
United States, domestic				
erude	. 483	570	742	750
United States, refined from	a			
foreign and domestic	ا ر			
matte and buffion (d).	(d) 1.100	2,905	5,753	2,256
Borneo and Sumatra and	1			
other ernde (e)	. 200	(f)	(f)	(f)
Total	. 268,108	263,453	148,898	92,488

(a)Estimated. (b) In addition to platinu.. contained in matte and bullion refined in the United States. (c) Chiefly iridosmine. (d) Does not include refined platinum from domestic crude. (e) Includes small production in Madagascar. (f) No basis for estimate.

Canada has up to the present been of very minor importance as a producer of this metal. A few hundred ounces are recovered annually from the refining of Sudbury copper-niekel matte by the International Nickel Corporation in the United States, and probably a somewhat larger amount by the Mond Nickel Company at their refinery in England. In this connection it is interesting to note that the Mond Nickel Company are reported to be making a better recovery of platinum metals by their process of refining than the International Nickel Corporation have so far accomplished at their New Jersey works.

The report of the Royal Ontario Niekel Commission states that in 1916 the matte produced by the Canadian Copper Company was estimated to contain 5,640 ounces of platinum and 8,460 ounces of palladium, and that the recovery of these metals by

766-0.

11

~

the International Niekel Company in that year amounted to 1,-093 ounces of platinum and palladium together with 257 onnees of other metals of the platinum group. Recent research investigations conducted by the International Niekel Company have shown that it is possible to greatly improve their recovery of the platinum group metals and it is probable that these improved methods will be practiced in the near future. The Mond Nickel Company did not furnish figures of platinum recoveries to the Royal Ontario Nickel Commission, but from assays made by the Commission it would appear that the Mond Nickel Company's matte contained more of the platinum group metals than the matte of the Canadian Copper Company.

The British America Nickel Corporation will employ the Hybinette process of electrolytic refining, which it is expected will make a more or less complete recovery of the precious metals in the matte.

Should the International Nickel Company succeed in recovering a high proportion of the precious metals it is well within the range of possibility that the total production of platinum group metals by the three nickel companies will exceed 10,000 onnees yearly.

Some years ago a considerable quantity of native platinum was produced from the Tulameeu District in British Columbia. There are no data of the amount produced previous to 1885, but since that date the platinum recovered has been estimated by Camsell at 10,000 to 20,000 ounces¹, and at one time this district was the principal producer of platinum in North America.

In view of the serious shortage in the world's supply of platinum, and mean especially because of its importance as a war metal, the Looper Tunitions Board, in June, 1918, requested the Munitical Lees Commission to undertake an examination of certa. Letinum occurrences in Alberta and British Columbia

One of the first properties to be examined was at Fort Saskatchewan, Alberta, on the Saskatehewan river. The owners of this property having applied to the Imperial Munitions Board for examination of the ground, and subsequent financial assistance, if sufficient platinum were discovered, the Commission was asked to undertake a systematic examination of the property, and to report thereon at the earliest possible moment. Dr. W. L. Uglow, of the Commission staff, was sent to Fort Saskatchewan early in June, and made a preliminary report

¹Memoir No. 26. Geology and Mineral Deposits, Tulameen District, B.C., G.S.C., 1913.

 \mathbf{t}_{i}

to the effect that both gold and platimum were found to occur, although it was difficult to estimate the value of the ground by sampling methods employed in the preliminary examination. It was then decided to survey and drill the property in m approved manner in order to demonstrate beyond any uncertainty the possibility of platinum production, and an Empire Drill was placed at Dr. Uglow's disposal for this purpose. Pending the arrival of the drilling equipment at Fort Saskatehewan, Dr. Uglow was instructed to make a quick trip up the Peace River for the purpose of investigating certain alleged platinum discoveries in the vicinity of the junction of the Finlay and Parsnip rivers with the Peace river. His report on the possibility of securing platimum in the Peace River District was not optimistic, and he returned to Fort Saskatchewan and commenced the drilling of the later property, early in the month of July.

Drilling was continued at Fort Saskatehewan until about the middle of Angust during which time 22 holes were put down with the Empire Drill, of whice, 18 were sunk to a hed-rock consisting of elay shale. The Fort Saskatehewan work may be briefly summarized as follows:

The gold and platimum occur in the form of a very small flat flakes or scales rather larger than the fiftieth of an inch in their largest dimensions, and therefore their recovery by dredging operations would be very difficult. The gravel which carries the precions metal has an average thickness of about 11 feet, and covering a very large proportion of this gravel is a mantle of fine sand silt with an average thickness of 161/2 feet. The flakes of the precions metals were found to lie eldefly in the upper 4 or 5 feet of the gravel, and therefore their recovery would require the entire removal of the overlying mantle of silt which itself is almost quite barren. The samples, with one or two exceptions, were found to contain less than 10 cents in gold and platinum per enbie yard of gravel, and while there are smaller and shallow stretches of the gravel on the river bars which yield values from 12 to 58 cents per cubic yard, the property as a whole was not considered valuable for large scale dredging operations.

Meanwhile, early in August, the writer, in company with Mr. Charles Camsell of the Geological Survey, made a eareful examination of the stream gravels of the Tulameen river, British Columbia, and concluded therefrom that this stream should be prospected by means of core drills to determine its value as dredging ground. The town of Tulameen is situated in the Similkameen Mining Division in south-western British Colum-

bia, and is reached from Vanconver via Ruby Creek Junction and Kettle Valley railway. The Tulameen river is a small mountain tributory of the Similkameen river forming a junction with the latter stream in the vicinity of the town of Prineeton. In the early days the Tulameen was worked energetically for placer gold and a considerable amount of platinum was also secured in the past, but as the price of this metal at the time of early mining operations was only from \$5 to \$10 an ounce, its recovery was not given much attention.

During the preliminary survey of the Tulameen some small seale washing operations were conducted with the object of securing a rough estimate of the value of the ground. In these tests about 90 cubic yards of gravel were washed and the small clean-up made therefrom was distinctly encouraging. The gold and platimum were found to occur in approximately the proportions of 60% of the former to 40% of the latter, both metals being in rather small grains and flattened seales, although there was sufficient evidence from the character of these 3main particles to point to the fact that the metals had not travelled far from the source of their origin.

Both Cansell and Kemp have described the occurrence of platinum in this district exhaustively, and there is no need of further amplification. Both of these investigators determined the fact that platinum originated with the pyroxenite rocks of the district associated with chromite and magnetite. It is interesting to note in this particular that we were shown several small nuggets of platinum encrusted with chromite which the unitiated might readily mistake for pure chromite or magnetite. When these small enernsted nuggets were immersed in dilute nitric acid for a short time the coating of chromite was dissolved away leaving the kernel of platinum.

During onr investigation in the field, there were no large muggets of platinum discovered, but we were shown a very fine collection of nuggets, the property of a Mrs. Cook, of Coalmont. The largest of the Cook nuggets was about the size of a large kernel of eorn, and the smallest about the size of a grain of wheat. These nuggets have been on exhibition at various times and as they are a very unique collection they should be acquired for the museum of the Department \uparrow Mines in Ottawa.

The upper portion of the Julameen river lying above the mouth of Slate ereek has a more or less eanyon-like character, the banks being very steep and precipitous, and this portion of the river is being worked at the present time by prospectors for the recovery of the precions metals. Some of these prospectors are working the high benches from 50 to 100 feet above the

ereek bottom; others are attempting to recover the gold and platimum from pot-holes in the river bed but the sam total of their operations is rather small, and the production of precious metals is almost negligible, making little better than wages for the operators.

Below the month of Slate ereck, and for three miles down stream to the town of Tulameen, the character of the river is decidedly different. The river valley broadens to an average width of 900 feet and the gravel lies in large bars and low-lying benches at depths that vary from 20 to over 100 feet. It was this area that was considered should be prospected by means of core drills. The total quantity of gravel has been estimated roughly at 15,000,000 enbic yards, most of which consist of heavy coarse pebbles with many bondders the size of a football. Occasionally, large bonders the size of an automobile are encoantered, but they are by no means numerous, and should not present any serions difficulty in dredging operations.

The Kettle Valley Railway touches the Tulameen river at the town of Tulameen, three and a half miles below Slate creek, and follows the river for a distance of approximately 20 miles down stream to the town of Princeton. The question of trans portation is therefore solved. The river bed between the town of Tulameen and Slate Creek is not heavily timbered, although there is some quantity of poplar and jack pine with an oceasional good-sized sprnce and more rarely fir and red and white pine. The river has a fall of 116 feet between Slate creek and the town of Tulameen and flows for the most part of this distance in a series of small rapids interspaced with quiet stretches with an average speed of approximately five miles per hour. The stream is not deep-probably the deepest holes at the foot of the numerous small rapids are not greater than 15 feet, whereas the average depth of the river at low water is about 11/2 feet. The river, like all mountain streams, is very turbulent in the spring of the year, but this condition should not seriously affect dredging operations if due precautions are taken.

Drilling with the Empire hand equipment was commenced in the month of September, and after the completion of three holes, the deepest being 62 feet, it was decided to install a power drill of the Keystone type, as the gravels were too heavy and tight to allow of much speed being made with the Empire equipment.

The chief advantage of the Empire hand drill is its mobility. It will take down so that the largest piece to be transported does not weigh more than 250 lb., and providing that the gravels to be examined are not heavy or contain too many bould-

ers considerable progress can be made with this equipment. The manufacturers claim that the essential feature of the Empire is the rotation of the casing during the entire drilling operation. A platform is mounted on the top of the casing upon which four labourers stand and alternately lift and drop the drill rods to which are attached the drilling tools. Providing the ground is not very tight and does not consist of heavy gravel, the rotation of the casing by means of horsepower together with the weight of the equipment and the men on the platform will sink the casing as trilling proceeds, and the core of sand and gravel accumulated in the inside of the easing is pumped out as fast as it forms.

A power drill of the Keystone type works in somewhat different manner. The easing is driven into the ground for every foot made and as a general rule progress is made by alternately driving for one or more feet and then pumping the core accumulated from the previous driving. When exceptionally large boulders are encountered, drilling below the casing is resorted to and is generally permissible. The Keystone casing is larger and heavier than the Empire, and is driven by means of two steel driving-blocks bolted to the drilling stem, the total weight of which is approximately 800 pounds. In driving, some fifty to sixty blows are struck per minute with a fall of approximately fourteen inches, and it is an exceptionally large boulder that cannot be drilled through, broken up or pushed to one side by this heavy and continuous pounding.

When starting with the Empire drill it was quickly denonstrated that the ordinary Empire method of working would not make progress in heavy gravel, and it was therefore decided to erect a tripod over the drill platform and with a sordinary plan driver trip employ a 500 pound driving block of the in order to drive the easing in the same manner as a Keystone casing is driven. With this equipment, and using a horse to lift the driving block from two to four blows were struck per minute, considerably better progress was made than by allowing the easing to sink simply by rotation. Notwithstanding this additional equipment the Empire could not keep pace with the Keystone, and the power drill was eventually used exclusively.

Drilling was continued until the second of December when a heavy fall of snow held up operations, and as no provision had been made to continue during the winter months, the work was stopped and the outfit stored in Vancouver.

From the comparatively small amount of work accomplished it is difficult to arrive at definite conclusions regarding the value of the Tulameen gravels, but it can be stated that results.

incomplete as they are, warrant further investigation. Altogether cleven holes were put down, the deepest being 72' 6", and the shallowest 11' with a total of 516' drilled. Six holes were put down to bed-rock, the others being stopped at depths at which the values did not warrant further drilling. Bed-rock was found to consist of a rather hard green quartz-schist, which on panning yielded no black sand but abundance of fresh iron pyrites. Both gold and platimm were found to occur in small scales and pellets with an occasional colour of gold of approximately 1/2 milligram weight. Platimum in the ore samples could not be distingnished from drill steel cuttings, and therefore no log could be made of its occurrence during drilling operations. Gold colours, however, were logged in the customary manner.

÷

Core samples consisting of the total amount of black sand from each hole were forwarded to the Dominion Assay Office, in Vaneonver, and in every ease the total amount of sample was melted down for assay. This entailed a great deal of work, but was considered necessary because of the difficulty in aeenrately entting down to assay ton samples. No attempt was made to amalgamate gold in the field because in the recovery of both gold and platinum by large scale operations ordinary methods of amalgamation would not apply.

In addition to the Tulameen work the Commission engaged Mr. Wm. Thomlinson of New Denver, to undertake the sampling of a large number of specimens from many localities in sonthern British Columbia where platinum had been reported or was supposed to occur. An alleged occurrence of platinum and gold on Potato ereek, Jervis Inlet, a short distance north of Vanconver, was examined and reported npon.

A detailed report of all platinum work completed including drill logs and surveys will be published by the Commission early in the summer of this year.

MANGANESE.

In the month of Angust last, the writer, at the request of the Canadian War Trade Board undertook an examination of a new discovery of manganese ore situated near Lake Cowiehan at the summit of the divide between Chemainus and Cowiehan rivers, on Vancouver Island.

At the time of the first visit the small amount of stripping accomplished had disclosed the outcrop of a secondary deposit of manganese oxide for a distance of approximately 100 feet, striking 10° south of west, and dipping 70° towards the south.

The deposit lies near the contact of the Sicker series and the Cowichan group, described by C. H. Clapp, in map 17A of

south Vancouver Island, published by the Geologieal Survey. The ore-body appears to be associated with the quartzite rocks of the Sieker series and consists of maganite and possibly some psilomelane which has undoubtedly been derived from the alteration of rhodonite, the silicate of manganese, which is strongly in evidence on both sides of the ore-body. Samples taken aeross the widest portion of the outcrop indicated approximately 12 feet of ore with a metallic manganese content of better than 50%, and with less than 15% of silica. Phosphorus was found to be present in amounts generally less than .075%.

The report to the War Trade Board was to the effect that the deposit consisted of a promising prospect of merchantable metallurgical ore, and that the owners were prepared to develop their property under certain guarantees providing for the marketing of the ore produced. The War Trade Board, after some considerable delay in consideration of the proposal, eventually declined to furnish the required guarantees, and no production of ore has taken place to date.

4

.

A second inspection of this property was made on the 11th November, and as considerably more stripping had been accomplished at this later date a much better opportunity was given of securing representative samples which on analyses proved to parallel very closely the results from the first set of samples obtained in Angust.

Unfortunately, the owners contented themselves with merely stripping the surface, and while they have disclosed a very attractive outerop of high grade metallurgical ore they had not during 1918 accomplished any cross-cutting or sinking to prove the quality of the ore at depth. This, of course, is to be regretted, as in all secondary deposits of this nature, particularly of manganese, the deciding factor as regards the value of the deposit is the extent to which oxidation of the original mineral has taken place. That the owners realize the importance of this is indicated by the fact that they are now engaged in removing portions of the outerop to prove the quality of the ore for at least 10 feet below the surface.

If the Cowiehan deposits are proved to contain a large tonnage of metallurgical ore such discovery would be of considerable importance to the iron and steel interests of this country. At the present time, Canadian iron and steel works are using something over 1.000 tons monthly of ferro-manganese, all of which is imported either from England or the United States, and therefore if a domestic supply of manganese ore can be assured its utilization should be carefully investigated. The situation of the deposits with respect to the market in Eastern

Canada is unfortunate, and it is a matter of doubt whether it would be advisable to manufacture ferro-manganese on the coast, or transport the ore by boat to Atlantic ports via the Panama Canal. The prospect for the manufacture of ferromanganese on the coast possesses several attractive features and one outstanding problem, which is the cost of electric power. According to figures given to the writer and also quoted by Dr. Stansfield in his report on the iron smelting possibilities in British Columbia, electric power is quoted at a considerably higher figure than would admit of proftable electric smelting, even in the case of ferro-manganese.

The Commission intends to publish very shortly all information at its disposal on the Cowiehan manganese deposits, and the possibilities of manufacturing therefrom in Canada high grade ferro-manganese.



